



DIAMOND IDENTIFICATION REPORT

NUMBER 389982883 September 25, 2019

DESCRIPTION NATURAL DIAMOND
SHAPE AND CUT ROUND BRILLIANT

CARAT WEIGHT 0.08 CARAT

COLOR GRADE F

CLARITY GRADE VVS 2

CUT GRADE VERY GOOD

POLISH VERY GOOD

SYMMETRY GOOD

Measurements 2.83 - 2.86 x 1.71 mm

Table Size 60%

Crown Height - Angle 14% - 35°

Pavilion Depth - Angle 43.5% - 41.3°

Girdle Thickness THIN TO MEDIUM

Culet MEDIUM

FLUORESCENCE NONE

I.G.I. employs and utilizes those techniques and equipment currently available to I.G.I., including, without limitation, 10X magnification corrected triplet loupe and binocular microscope, master color comparison diamonds, non-contact-optical measuring device, and such other instruments and/or processes as deemed appropriate by I.G.I. A duly accredited gemologist or jeweler can advise you with respect to the importance of and interrelationship between cut, color, clarity and carat weight.

CLARITY SCALE

| FLAWLESS/ INTERNALLY FLAWLESS | VERY VERY SLIGHTLY INCLUDED | | VERY SLIGHTLY INCLUDED | | SLIGHTLY INCLUDED | | IMPERFECTION | | |
|-------------------------------------|-----------------------------------|------------------|---------------------------|-----------------|----------------------|-----------------|----------------|----------------|----------------|
| | VVS ₁ | VVS ₂ | VS ₁ | VS ₂ | SI ₁ | SI ₂ | I ₁ | I ₂ | I ₃ |

COLOR SCALE

| COLORLESS | | | NEAR COLORLESS | | SLIGHTLY TINTED | | VERY LIGHT YELLOW | | | | | LIGHT YELLOW | | | | | FANCY COLOR | | | | | |
|-----------|---|---|-------------------|---|--------------------|---|-------------------|---|---|---|---|--------------|---|---|---|---|----------------|---|---|---|---|---|
| D | E | F | G | H | I | J | K | L | M | N | O | P | Q | R | S | T | | U | V | W | X | Y |

O-m Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.



See limitations
and restrictions on reverse

© I.G.I., 2000, edition 2011

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute